


Basic Chrome Sulphate



Description:	Basic Chrome Sulphate (Dry Chrome Tanning Agent)
Appearance:	Green powder
Application:	Leather Industry, Fur Industry
CAS No:	12336-95-7

Technical Data

Specification	Norm	
	Low basicity	High basicity
Chromium Oxide (Cr ₂ O ₃), %, min	25	25
Basicity (Schorlemmer), %	33±1	40±1
Water insoluble residue, %, max	0,1	0,1
Iron calculated as FeO, %, max	0,04	0,04
pH (2% solution)	3,0 ± 0,3	3,0 ± 0,3
Hexavalent Chromium (Cr ⁶⁺), ppm	Not Detected	Not Detected

Features and advantages:

- soft tanning, giving the leather fineness and softness
- prevention of the outer layer overtanning
- rapid penetration of the tanning agent into the deep layers of leather
- high percentage of chromium binding during leather tanning

Packaging:

Single-trip flexible intermediate bulk containers with a net weight of 600 kg; PE lined multiwall paper bags with a net weight of 25 kg.

Storage:

To be stored in tightly closed vessels in a roofed area, at temperatures 0-50 °C.

Shelf life:

12 months from the date of production

Transport requirements:

Limitations resulting from ADR, RID and IMDG regulations do not apply. Any means of transport can be used. No special precautions are required.

623104, Zavodskaya str., 3, Pervouralsk, Sverdlovsk region, Russia
+7 (910) 083 46 43 (WhatsApp) | abikmullina@polyplast-un.com
www.chrompik.com

The information contained herein is presented in good faith and to the best of our current knowledge and experience. The compliance of specific properties of the supplied product with the data given herein and its fitness for the intended purpose should be verified before the product is applied. Producer reserves the right to modify the information presented herein as a result of technological development and improvement of the product.